

Technical Data	All Purpose Caulk Clear	All Purpose Caulk White & Colors	Drywall, Panel & Foam Adhesive	Test Method
Viscosity	700,000 - 1,200,000 TF spindle @ 4 rpm	425,000 - 625,000 TF spindle @ 4 rpm	200,000 +/- 100,000 cps TF spindle @ 20 rpm	Brookfield RVF 50% RH 73° F
Tack Free Time	25 +/- 15 minutes	50 +/- 20 minutes	60 +/- 20 minutes	ASTM C-679 50% RH, 73° F
Elongation at break	400 - 500%	300 - 350%	225 - 275%	ASTM D-412
Hardness Shore A	27 - 33	15 - 19	27 - 33	ASTM C-661
Shear strength	190 - 200 psi	110 - 130 psi	190 - 200 psi	ASTM D-1002
Peel Value	15 - 20 pli Glass	4 - 5 pli Glass 3 - 4 pli Concrete	5 - 6 pli Glass 8 - 9 pli Concrete	ASTM C-794
Density	8.5 +/- 0.2 lbs / gallon	11.1 +/- 0.2 lbs / gallon	11.0 +/- 0.5 lbs/gallon	ASTM D-1475
VOC Content	14 grams / liter	18 grams / liter	20 grams / liter	ASTM D-2369

Technical Data	Painters Caulk	Construction Adhesive	Test Method
Viscosity	100,000 - 300,000 TD spindle @ 4 rpm	800,000 - 1,250,000 TF spindle @ 4 rpm	Brookfield RVF 50% RH 73° F
Tack Free Time	40 +/- 10 minutes	25 +/- 5 minutes	ASTM C-679 50% RH, 73° F
Elongation at break	270 - 300%	90 - 110%	ASTM D-412
Hardness Shore A	25 - 30	55 - 65	ASTM C-661
Shear strength	190 - 200 psi	500 - 600 psi	ASTM D-1002
Peel Value	14 - 16 pli Glass 14 - 15 pli Concrete	NA	ASTM C-794
Density	9.5 +/- 0.2 lbs / gallon	11.5 +/- 0.5 lbs / gallon	ASTM D-1475
VOC Content	19 grams / liter	32 grams / liter	ASTM D-2369

THEORETICAL YIELD
Per 10.3 fl. oz. Cartridge Joint Size Linear Feet
1/4" x 1/4" 25
1/4" x 3/8" 17
1/4" x 1/2" 12
1/2" x 3/8" 8.5
1/2" x 1/2" 6.5
3/4" x 1/2" 4